


Bs-Temperature


H=1194A/m




Initial permeability	μ_i	25°C	3200±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
		100°C	420
Remanence	Br(mT)	25°C	130
		100°C	80
Coercivity	Hc(A/m)	25°C	11
		100°C	10
Core loss	Pcv(kW/m ³)	25°C	350
		100kHz 200mT	250
		100°C	660

Temperature	25°C	100°C
resistivity	$\rho(\Omega\cdot m)$	3
	d(kg/m ³)	4.8×10^3


: Toroid(mm)
: 25
: 15
: 7.5



μ_i -Temperature



μ_i -Frequency



B-H

